



(12)

EUROPEAN PATENT APPLICATION

(21) Application number : **94302942.1**

(51) Int. Cl.⁵ : **C09D 11/20**

(22) Date of filing : **25.04.94**

(30) Priority : **05.05.93 GB 9309184**

(43) Date of publication of application :
09.11.94 Bulletin 94/45

(84) Designated Contracting States :
**AT BE CH DE DK ES FR GB GR IE IT LI LU MC
NL PT SE**

(71) Applicant : **IMPERIAL CHEMICAL
INDUSTRIES PLC**
Imperial Chemical House,
Millbank
London SW1P 3JF (GB)

(72) Inventor : **Van Lint, Greg**
Kalverstraat 50
B-3320 Hoegaarden (BE)
Inventor : **Bebbington, Samuel Thomas**
16 Evesham Walk,
Middleton
Manchester, Lancashire M24 1PW (GB)

(74) Representative : **Ede, Eric et al**
Imperial Chemical Industries PLC,
Group Patents Services Department,
P O Box 6,
Shire Park,
Bessemer Road
Welwyn Garden City Herts., AL7 1HD (GB)

(54) Indelible ink formation.

(57) A stable indelible coloured ink composition for invalidating bank notes or similar valuables by staining them permanently, comprises at least one of di- or tri- phenylguanidine.

EP 0 623 658 A2

The present invention is directed to an ink composition and the use of such composition for invalidating bank notes or similar valuables by staining them permanently.

As a protection against fraud, it is known to incorporate diphenylguanidine, preferably complexed with various agents, as colourless ink in valuable papers that will develop a conspicuous colour for example during attempted erasure by bleaching cheques.

Diphenyl-guanidine will indeed provide a conspicuous stain in the case ink eradicators such as oxidising agents (typically sodium hypochlorite) are used during an attempt to remove the dye and/or the pigments which have been sprayed or sprinkled on the valuables.

In the above prior art the inks were used for safety papers at the manufacturing or printing steps.

However, there is a need for a coloured ink formulation stable for a long period of time and within a large range of temperature which produces stable and permanent stain that cannot be leached by current agents such as sodium hypochlorite.

According to the invention, there is disclosed a stable ink formulation adapted for use in security devices such as in bank notes dispensers or transportation systems. For this purpose, the formulation must be stable for a long time in the wide range of temperature as encountered by the above dispensers located in public places and operating in winter or summer periods.

According to the invention, it has been found that a di- or triphenylguanidine may advantageously be incorporated in a coloured ink which will meet the above requirement.

According to a particular embodiment, the ink formulation contains a dye, a pigment, a dispersant and a di- or tri-phenylguanidine in a suitable organic solvent.

Surprisingly, it has furthermore been found that the above combination will result in a stable ink providing maximum penetration of a block of banknotes and permanent stain that cannot be leached using all available techniques.

The formulation, incorporated in a suitable device, will in operation colour extensively the stack or bundle of bank notes in a container, the action of the ingredients being complementary. A device suitable for this purpose is disclosed in our co-pending application No. 943 entitled "Device for Bank Note Containers" (NEC.37554/EP).

The dye will perform in depth while the action of the pigment is more permanent and tenacious but will be more limited to the surface, the diffusion thereof being limited. The above combination results however in a synergistic effect as to the stability of the resulting stain.

A particularly suitable formulation in accordance with the invention comprises:

- an alcohol type soluble dye (0.5-3% by weight)
- a pigment (0.1-1%)
- a surface active agent being a dispersant compatible with the pigment (2-5%)
- diphenyl guanidine (5-15%)
- a compatible organic solvent (76-92%)

Preferably the organic solvent is an alcohol based solvent, such as industrial methylated ethanol.

Preferably the surface active agent is a polyoxyalkylene amine derivative.

According to a particularly preferred embodiment of the invention the formulation comprises, in the above ranges of concentration:

- Lampronol Red 2BRN (C I Solvent Red 122)
- Solsperse 20.000
- Monolite Rubine 3B
- diphenyl guanidine
- industrial methylated spirits 74 OP

Lampronol, Solsperse and Monolite are ICI PLC trademarks.

The formulation according to the invention is obtained by simply mixing the various components according to the methods well-known in the art.

Diphenylguanidine is commercialized under the trademark Perminal (ICI PLC, Francolor).

A particularly suitable formulation comprises (weight %):

1.5-2.2%	Lampronol Red 2BRN
0.3-0.7%	Solsperse 20.000
2.8-3.8%	Monolite Rubine 3B CI
8-12%	diphenyl guanidine
81-87%	industrial methylated spirits 74 OP

Example:

A formulation is prepared according to the known techniques of mixing ingredients for manufacturing inks, containing the following ingredients:

- 5 appr.
 2.0% Lampronol Red 2BRN
 0.5% Solsperse 20.000
 3.5% Monolite Rubine 3B CI
 10% Permal DPG (N.O.T.)
 10 84% Industrial methylated Spirits 74 OP81

A bundle of 1000 test banknotes have been stained by the above formulation using a conventional sprinkling device incorporated in a preloaded banknotes cassette. The stains (Bordeaux) covered more than 20% of the surface of the banknotes.

- 15 Attempts to remove the stain coloration have been unsuccessfully performed, 15 minutes and 24 hours after staining, using the following agents:

ethanol, acetone, trichloroethylene, chloroform, ethyl acetate, white spirit, dimethylformamide, Javelle water, vinegar, acetone + chloroform + sodium or potassium hypochlorite (successively), hydrochloric acid and various washing compositions (detergents at 95°C). In the worse cases, a rose or yellow coloration was maintained and/or the texture of the paper and the printing ink used for its manufacture were severely and noticeable altered.

Claims

- 25 1. A coloured ink formulation *characterised in that* it comprises di- or triphenylguanidine.
2. An ink formulation according to claim 1 for sprinkling wherein the di or triphenylguanidine is present in an amount of from 2 to 20% by weight.
- 30 3. An ink formulation according to claim 1 or 2 *characterised in that* it comprises at least:
- 0.5-3% by weight of an alcohol type soluble dye
 - 0.1-1% of a pigment
 - 2-5% of a surface active agent being a dispersant compatible with the pigment
 - 5-15% of a triphenyl or diphenyl guanidine
 - 35 - 76-92% of an organic solvent.
4. A formulation according to claim 3 wherein the dye is an azo-chrome complex dyestuff.
5. A formulation according to claim 3 wherein the dye is a C I solvent red 122 dye.
- 40 6. A formulation according to claim 3 wherein the surfactant is a polyoxyalkylene amine derivative.
7. A formulation according to any one of the preceding claims *characterised in that* it comprises, by weight, at least:
- | | |
|----------|--------------------------------------|
| 1.5-2.2% | Lampronol Red 2BRN |
| 0.3-0.7% | Solsperse 20.000 |
| 2.8-3.8% | Monolite Rubine 3B CI |
| 8-12% | diphenyl guanidine |
| 81-87% | industrial methylated spirits 74 OP. |
- 45
8. Use of an ink formulation according to any of the preceding claims for sprinkling onto paper valuables in security containers.
9. Use according to claim 8 wherein the valuables are bank notes stacked in a rechargeable cassette.
- 55 10. A method of permanent marking of paper valuables comprising contacting the paper valuables with a coloured ink formulation according to any one of claims 1 to 7.